

1.4938, X12CrNiMoV12-3, UNS S64152, M152 - Turbine Blade Steels Datasheet

1.4938, [X12CrNiMoV12-3](#) is a high-alloy Cr-Ni-Mo High temperature high strength Martensitic Stainless steel, add of V (vanadium) for carburization with a martensitic structure, which due to high strength properties and significantly increased resistance to oxidation, is used for the production of aviation propellers, especially loaded gears, ball screws, responsible parts working at elevated temperatures such as rotors and turbine blades, bolts in the power industry, pump components as well as coupling parts in aircraft constructions. Unique composition chemical composition ensures high hardenability, great naw glonej layer parameters (hardness, toughness), and a clear reduction in deformations arising during heat treatment. ESR (Electro Slag Remelted)

Chemical Composition

Grade	Chemical Composition WT %									
	C	Mn	Si	P	S	Cr	Mo	Ni	V	N
Jethete® Alloy Steel M152	0.08-0.13	0.50-0.90	Max 0.35	Max 0.030	Max 0.025	11.0 - 12.5	1.5 - 2.0	2.0 - 3.0	0.25 - 0.40	0.02 - 0.04
X12CrNiMoV12-3 MOD(SK ODA)	0.08 - 0.15	0.50-0.90	Max 0.35	Max 0.020	Max 0.015	11.0 - 12.5	1.5 - 2.0	2.0 - 3.0	0.25 - 0.40	0.02 - 0.04
1.4938, X12CrNiMoV12-3	0.08 - 0.15	0.4 - 0.9	Max 0.5	Max 0.025	Max 0.015	11.0 - 12.5	1.5 - 2.0	2.0 - 3.0	0.25 - 0.40	0.02 - 0.04
1.4939, X12CrNiMo12, X12CrNiMoN12	0.08 - 0.13	0.5 - 0.9	Max 0.35	Max 0.025	Max 0.020	11.0 - 12.5	1.5 - 2.0	2.0 - 3.0	0.25 - 0.40	0.02 - 0.04
X11CrNiMoN12	0.08 - 0.15	0.4 - 0.9	Max 0.50	Max 0.025	Max 0.015	11.0 - 12.5	1.5 - 2.0	2.0 - 3.0	0.25 - 0.40	0.02 - 0.04
AMS UNS S64152	0.08 - 0.15	0.5 - 0.9	Max 0.35	Max 0.025	Max 0.025	11.0 - 12.5	1.5 - 2.0	2.0 - 3.0	0.25 - 0.40	0.01 - 0.05
Z12CND V12-03	0.08 - 0.15	0.5 - 0.9	Max 0.35	Max 0.030	Max 0.015	11.0 - 12.5	1.5 - 2.0	2.0 - 3.0	0.25 - 0.40	0.02 - 0.04
XM-32	0.08 - 0.13	0.5 - 0.9	Max 0.40	Max 0.030	Max 0.025	11.0 - 12.5	1.5 - 2.0	2.0 - 3.0	0.25 - 0.40	0.02 - 0.04

Mechanical Properties

- Tensile strength, Rm: 900 - 1100 MPa
 - The yield point, R_e: > 785 MPa
 - Elongation, A: >14%
 - Reduction of area Z %, for information
 - Impact resistance, KV₂₀ : > 40 J
-
- Tensile strength, Rm: min 155ksi(1069 MPa)

- The yield point, R_e : min 130ksi(896 MPa)
- Elongation in 4D min 12%
- Reduction of area Z min 30%
- Charpy Impact value, Shall be not less than 30 ft-lb (41 J), determined on the V-notched specimen at room temperature.
- Hardness: should be 341 to 375 HBW, or equivalent (see 8.2). Product shall not be rejected on the basis of hardness if the tensile properties determined on specimens taken from the same sample as that with nonconforming hardness or another sample with similar nonconforming hardness, are acceptable
- Average Grain Size: Shall be ASTM No. 4 or finer, determined in accordance with ASTM E112

- Tensile strength, R_m : 930 - 1130 MPa
- The yield point, R_e : > 760 MPa
- Elongation, A: >14%
- Impact resistance, KV_{20} : > 40 J
- Contraction, Z: >40%
- Hardness in softening annealed condition: ~250 HB

Physical Properties

Physical Properties	Imperial	Metric
Density	0.28 lb/in ³	7.75 g/cc

Heat Treatment

Quenched and tempered to QT900 , minimum tempering temperature : 640 ° C . After quenching the part needs to be cooled long enough to ensure that the martensitic transformation of the microstructure is completed . Stress relieving after bending . Stress relieve temperature : 30-50 ° C below last tempering temperature. Min . holding time for tempering and stress relieving : 2 minutes / mm of bar thickness or . diameter It shall be guaranteed that the microstructure is quenched and tempered and homogeneous over the entire cross - section .

Bars, wire, forgings, flash welded rings, extrusions, and mechanical tubing shall be annealed by heating to 1400 ° F ± 25 ° F(760 ° C ± 14 ° C) maximum, holding at heat for not less than 6 hours, and cooling in air.

Welding Properties

Machining Properties

Similar or Equivalents Steel Grade

M152, 1.4938, X12CrNiMoV12-3, 1.4939, X12CrNiMo12, J2, X11CrNiMoN12, UNS S64152, Z12CNDV12-03, XM-32, 10Cr12Ni3Mo2VN, S47250, X13VD